

# NEOPRENE SLEEVES

Scheda Tecnica aggiornata al 22.09.2016 / pag. 1 di 1



## FEATURES

Abrasion resistance  
 Resistant to low temperature  
 Good resistance to oil and solvent  
 Resistant to humidity and ageing

## VERSION

● Black

## PACKAGING

Cut lengths

## MATERIALS

Neoprene

## FIELD OF USE

Operating temperature:  
 -30°C ÷ +90°C

Code	DIMENSIONS				PACKAGING
	Internal diameter	External diameter	Length	Wall thickness (NOM)	Bag
	mm	mm	mm	mm	pcs/bag
5380	1,3	2,0	20	0,5	1000
5381	1,8	3,5	20	0,5	1000
5381BIS	2,4	4,5	20	0,6	1000
5382	2,5	5,5	25	0,9	1000
5383	3,0	6,0	25	0,6	1000
5384	4,0	8,0	30	1,2	1000
5385	5,0	9,0	25	0,7	1000
5386	7,5	12,0	30	0,8	1000
5387	10,0	15,0	35	0,9	500
5388	12,0	20,0	50	1,2	500
5389	14,0	23,0	50	1,3	500
5390	17,0	28,0	50	1,3	500

## PHYSICAL PROPERTIES

Description	Test method	Typical value	UM
Tensile strength	ASTM D 638	>6,5	N/nm <sup>2</sup>
Elongation at break	ASTM D 638	>400	%
Tear strength	-	>10	kN/m
Hardness shore A	-	40±5	-

## ELECTRICAL PROPERTIES

Description	Test method	Typical value	UM
Dielectric strength	ASTM D 149	>13	kV/mm
Volume resistivity	ASTM D 257	4x10 <sup>9</sup>	W cm

## THERMAL PROPERTIES

Description	Test method	Typical value	UM
Flame resistance	UL94	V0	-
Short time operating temperature	-	110	°C